

PG – 15 E PRIMER

TWO COMPONENT TRANSPARENT EPOXY BASED PRIMER

DESCRIPTION

PG- 15E Primer is a low viscosity penetrating primer. It can be used as primer for polysulfide sealants

USES

As a primer coat on cement, concrete substrates, unglazed edges of ceramic tiles, natural and artificial; stones, bricks, asbestos cement to obtain proper adhesion between joint surface and sealant.

ADVANTAGES

- Low viscosity aids penetration
- Good adhesion

PROPERTIES

	@ 25 ° C
Density	0.9 Kg / Lit
Pot life	> 6 hrs
Tack free time	< 2 hrs

DIRECTIONS FOR USE

Surface preparation

All joints must be clean dry and free from all previous sealers, grease, oil and other contaminants, which may impair bond. Remove surface laitance by Sand Blasting or by other Mechanical means. Vacuum surface to remove all dust and debris. Newly constructed concrete surface should be cured as per construction norms.

Mixing

Stir each component separately in original packing with a slow speed drill. Empty the components B in component A and mix it for 2-3 Minutes or until uniformity with a slow speed drill.

Ratio : 60 part A : 40 part B by weight

PG -15 E primer kit is supplied in preweigh packs and do not add solvent or thinners. Application temperature 10°C to 40°C

Application

Apply by brush, roller or airless spray equipment

COVERAGE

PG 15E Primer 10 – 12 m²/ Liter

CLEANING OF TOOLS

Clean the tools with **CAP THINNER** immediately after use, remove uncured **PG 15E Primer** from tools and equipment by using **CAP THINNER**

Cured material may only be removed mechanically

PACKAGING

PG 15 E Primer : 1 liter Kit

CAP THINNER : 5 liter

STORAGE

PG 15E Primer should be stored under shade at temperatures between 10⁰ C to 30⁰ C.

SHELF LIFE:

12 months in sealed original container, under recommended storage conditions.

SAFETY PRECAUTIONS

Both components are flammable, keep away from direct flame and sources of ignition.

Keep container closed when not in use

Keep out of reach of Children

Both components are irritant, prolonged contact with skin or Eye may cause sensitization.

FIRST AID

Skin contact

Wash thoroughly with soap and water.

Eye contact

Flush immediately with clean water and seek medical advice

Respiratory Problem

Remove affected person to fresh air immediately and contact physician.

Hygiene

Wash hand immediately with **CAP THINNER** followed by soap and water.

PG – 15 E PRIMER

TWO COMPONENT TRANSPARENT EPOXY BASED PRIMER

TECHNICAL SERVICE:

Our Technical Service Department is available at any time to advise you in the correct use of this product or any other Ahlia products.

Note : The information presented herein is based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control.

As all Ahlia Technical Data Sheets are updated on a regular basis, it is the user responsibility to collect most recent issue.