

CAPSEAL

RUBBERIZED, EMULSIFIED BITUMEN PROTECTIVE COATING

DESCRIPTION

CAPSEAL is a rubberized bitumen protective coating specially formulated for corrosion protection and waterproofing of substrate including metals.

FEATURES

High grade rubberized bitumen-coating dries to a tough and resilient coating. The cured coating posses excellent adhesion to both cementitious and metal surfaces. As a curing membrane for hydration of cement.

STANDARDS

Complies with B.S 6949.

APPLICATIONS

CAPSEAL can be used as:

- General waterproof for most building materials including concrete, asbestos, cement, roofing felt, asphalt, wood, lead, zinc and corrugated iron.
- As a metal protector which provides protection against corrosion of pipes, steel structural works and other metallic surfaces.
- Protection of concrete foundations, retaining wall, column necks, ground beams and other structures liable to be back filled.
- As a curing membrane for hydration of cement.

ADVANTAGES

- Very effective on various substrates.
- Ready to use and easy to apply.
- Odorless and non toxic.
- Excellent adhesion on prepared substrates.
- Resists chemicals and salts.
- Effective on damp surfaces.

TYPICAL PROPERTIES

Appearance:

Dark brown liquid drying to black coating.

Density:

About 1.01 kg/litre.

Flash point:

Above 32°C.

Toxicity:

Non-toxic.

Service temperature limits:

Approx. upto 80°C depending on operating conditions.

Heat flow resistance:

The cured film will not sag or flow under service conditions.

Chemical and water resistance:

Resistant to water, salt water, dilute acids and alkalis.

Shelf life:

Minimum 12 months in sealed original containers, under recommended storage conditions.

COVERAGE

0.3 to 0.5 kg/m² per coat depending on irregularity and porosity of the substrate.

DIRECTIONS FOR USE

Surface preparation:

- Concrete surfaces must be clean, sound and free from oil, grease, dirt, dust and loose particles. It is desirable to dampen the surface with water if the concrete or block work is dry.
- Metal surfaces must be wire brushed to remove loose rust, mill scale etc. Wipe off oil and grease from the surface with a suitable solvent.
- It is recommended to use a primer coat of CAP-PRIME at the rate of 0.1 to 0.25 kg/m² to ensure proper bonding of subsequent coat.

CAPSEAL

RUBBERIZED, EMULSIFIED BITUMEN PROTECTIVE COATING

Method of Application:

- CAPSEAL can be applied by brush, broom or squeegee.
- Apply minimum two coat of CAPSEAL with a brush or broom.
- Each coat should be applied at right angles to the previous one to obtain proper coverage and uniformity.
- The first coat must be fully dry before the subsequent coat is applied. Normal drying time is between 1 to 4 hours. In conditions of high humid and cold weather, this may extend up to 12 hours or more.
- If required, blind the final coat with clean sharp sand while it is tacky. It improves heat resistance, premature ageing and atmospheric degradation.

CLEANING OF TOOLS

- Dip brush in clean water before and during use, for ease of application. During work break periods place them in water to prevent caking up of the bristles.
- Clean brushes and tools in soap and water immediately after use.

- Dried emulsion can be removed with the help of white spirit, petrol, diesel oil etc.

SAFETY PRECAUTIONS

- CAPSEAL is non-flammable and non-hazardous in normal use.
- When the product is wet, it should be removed from skin by soap and water. But when dry, suitable cleansers like petrol, diesel oil etc. should be used.
- Splashes to eyes should be washed immediately with abundant water.

PACKAGING

CAPSEAL is supplied in 15 kg pails and 200 kg drums.

STORAGE

- Store in sealed conventional containers, protected from extreme weather conditions.
- Stir well before use, if stored for a long time.

Rev. 01 August 2008

TECHNICAL SERVICE:

Our Technical Service Department is available at any time to advise you in the correct use of this product or any other Ahlia products.

Note : The information presented herein is based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control.

As all Ahlia Technical Data Sheets are updated on a regular basis, it is the user responsibility to collect most recent issue.